

Technical information

## EUROPLEX® PPSU sheet material

### EUROPLEX® PPSU sheets for rail interior applications

EUROPLEX® PPSU is a flame retardant sheet material based on polyphenylsulfone (PPSU). It shows excellent mechanical properties as well as good chemical resistance. The sheet series meets the fire standard requirements for many applications in public transport. The sheet is available in transparent and opaque colors (body colored). EUROPLEX® PPSU sheets are ideally suitable for vacuum deep-drawing and can be used for molded parts of window frames and for large scale wall and ceiling components. This meets the highest fire safety regulations in terms of burn-up speed, smoke gase density, heat release, and toxicity. EUROPLEX® PPSU sheet material meets the R1 requirement for Hazard level (HL) 3 rail vehicles as specified in the fire protection standard CEN/TS 45545-2:2009.



### Physical properties

Property	Test method	Unit	PPSU 99460 opaque	PPSU 99470 transparent
Density	ISO 1183	g/cm <sup>3</sup>	1.4	1.29
Vicat	ISO 306	°C	223	223
Max. service temp.		°C	195	195
Tensile strength	ISO 527	MPa	65	70
Tensile elongation	ISO 527	%	50	60-80
Modulus of elasticity	ISO 527	MPa	2600	2300
Charpy impact	ISO 179	KJ/m <sup>2</sup>	No failure	No failure
Transmittance	ISO 13468-1	%		45 at 4.0 mm

**Test results / R1 requirement / specification standard CEN/TS 45545-2: 2009**

Standard Test method	EUROPLEX® PPSU 99460 3.0 mm	EUROPLEX® PPSU 99460 1.0 mm	EUROPLEX® PPSU 99470 4.0 mm	EUROPLEX® PPSU 99470 2.0 mm
ISO 5660-1 Mahre (KW/m <sup>2</sup> )	5.3	8.5	84.3	51.3
ISO 5658-2 CFE (KW/m <sup>2</sup> )	46.2	49.3	37.9	42.8
ISO 5659-2 D s (4)	58	20	126	135
VO F 4	74	30	137	174
CIT 8 min	0.23	0.14	0.46	0.37



**Disclaimer** This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

August 2012

**Evonik Industries AG**

Kirschenallee, 64293 Darmstadt, Germany

PHONE +49 6151 18-4047, FAX +49 6151 18-3689, martin.russmann@evonik.de

www.performance-plastics.com www.evonik.com